

Directions for Use

Esthetic Glass Ionomer Cement for Filling

Oxford GI FILL E is a classical glass ionomer filling cement with improved esthetic and good physical properties. Besides its excellent fluoride release and excellent biocompatibility as glass ionomer cement Oxford GI FILL E also has good chemical bonding to dentine and enamel and a tight seal at the dentinal margins. Therefore it requires no enamel and dentine etching. Because of its radiopacity it ensures easy postoperative diagnosis. Oxford GI FILL E meets the requirements of: DIN EN ISO 9917-1 (Specification for Dental Water based Cements).

Indications

- Class I and II restorations in deciduous teeth
- Non-load bearing small class I and class II restorations in permanent teeth
- Intermediate restorative material for heavy stress situations in class I and class II cavities
- Base material for class I and II cavities according to sandwich technique
- Class V and root surface restorations
- Core build-ups

Contraindications

- Pulp capping
- In rare cases the product may cause sensitivity in some people. In these cases discontinue to use the product and consult a physician

Side effects

Side effects are not known to date

Application

1. Tooth Preparation

Prepare the tooth using standard techniques. Do not prepare thin edges.

If desired, place a matrix band.

Apply a conditioner according to the corresponding instructions to the bonding surfaces to remove the preparation smear layer. Rinse the conditioner thoroughly with water and dry gently. Do not desiccate.

Areas close to the pulp should be covered with a small amount of a calcium hydroxide liner (e.g. Oxford Cal).

2. Mixing

The **powder/liquid ratio** to achieve a suitable consistency is **3.6 /1.0**. This can be obtained by mixing **1 level (blue) scoop of powder and 1 drop of liquid**.

For accurate dispensing of **Oxford GI FILL E Powder** shake the bottle to loosen the powder. Overfill the spoon with the powder, level the powder by using the collar at the top of the bottle and carry it onto the mixing pad. **Avoid compressing** powder into the spoon with the inside wall of the bottle.

For dispensing of **Oxford GI FILL E Liquid** turn the bottle vertically with the tip about 5 cm above the mixing pad. Steady your hand and squeeze the bottle gently to dispense the drops. If any bubbles are present, lightly tap the bottle with the fingers holding it. **Discount drops** that contain bubbles and are obviously not full-sized.

Use a small spatula to rapidly mix all the cement powder into the liquid. Usually one scoop powder/ one drop liquid should provide for sufficient amount of mixed cement. The mixed cement should be thixotropic and have a smooth consistency and glossy appearance. Total mixing time is **30 sec.**

After use, tightly close both liquid and powder bottles to prevent exposure to moisture.

3. Filling

Mix the required amount of Oxford GI FILL E and apply it into the prepared cavity by using a suitable placement instrument. Please see to it, that no air bubbles will be incorporated.

Oxford GI FILL E should be placed in the cavity within the **working time (1:15 minutes from start of mixing at 23 °C or 74°F)**. If desired, a matrix band may be used to form the contour.

Net setting time is about **3:30 minutes**.

After setting, immediately apply Oxford GI COAT. Immediately light cure for 20 seconds.

Close bottle immediately after use.

Note:

Higher temperatures will shorten the working time; lower temperatures will prolong the working time.

An overextended working time will cause the loss of adhesion to the dental enamel and the dentine.

Remove the matrix when the cement has achieved clinical set (approx. **3:30 minutes** after application).

4. Finishing

Final finishing and polishing can begin from about **6 minutes** after start of mixing. Smooth with fine diamond burs, then polish with finishing and polishing discs with graded grain size.

Apply a thin layer of **Oxford GI COAT** to the final finished surface of the restoration. Immediately light cure for 20 seconds.

Close bottle immediately after use.

Instruct the patient not to expose the restoration to any pressure for one hour.

5. Conclusive Notes

The products are to be applied only by a dental professional in the manner as described in this instruction.

Do not use the products with patients who show an allergy to the material. In case of allergic reactions immediately stop the application, and advise the patient to consult a physician.

Do not allow the liquid or the mixture to contact the oral tissues or skin. In case of contact, remove the material with absorbent cotton soaked in alcohol and rinse with water.

Avoid eye contact of the mixture. In case of contact, immediately flush with water and seek medical treatment.

6. Storage

Store **Oxford GI FILL E** at room temperature (25 °C / 77 °F). Do not use after expiration date (expiration date see packaging).

Warranty

First Scientific Dental Materials GmbH warrants this product will be free from defects in material and manufacture. First Scientific Dental Materials GmbH makes no other warranties including any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining the suitability of the product for user's application. If this product is defective within the warranty period, your exclusively remedy and First Scientific Dental Materials GmbH's sole obligation shall be repair or replacement of the First Scientific Dental Materials product.

Limitation of Liability

Except where prohibited by law, First Scientific Dental Materials GmbH will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.

Keep away from children!

For dental use only!

Caution:

Federal law restricts the sale of this device to or by the order of a dentist.



Manufacturer:

First Scientific Dental Materials GmbH, 25335 Elmshorn, Germany

